

STAINLESS CMP FLATROLLED TOLERANCE TABLE
BASED ON MATERIAL WIDTHS OF 48", 60" & 72" WIDE

GAUGE	NOMINAL THICKNESS	TYPICAL	ASA THICKNESS RANGE	THICKNESS RANGE PER ASTM A484
7	0.187	0.181	.178 TO .188	.178 TO .207
8	0.17187	0.164	.161 TO .169	.161 TO .176
9	0.15625	0.148	.146 TO .152	.146 TO .160
10	0.134	0.131	.129 TO .135	.129 TO .1450
11	0.12	0.117	.114 TO .119	.1141 TO .1380
12	0.1054	0.101	.098 TO .103	.0981 TO .1140
13	0.09	0.083	.083 TO .087	.0831 TO .0980
14	0.0751	0.074	.072 TO .075	.0721 TO .0830
16	0.0595	0.058	.056 TO .054	.0565 TO .061
18	0.048	0.044	.044 TO .046	.044 TO .052
20	0.0355	0.034	.034 TO .036	.034 TO .038
22	0.0294	0.029	.028 TO .031	.028 TO .0316
24	0.0235	0.023	.023 TO .025	.023 TO .025
26	0.0178	0.0174	.0165 TO .019	.0165 TO .019
28	0.0151	0.0148	.014 TO .016	.014 TO .016
30	0.012	0.011	.010 TO .013	.010 TO .014

